

BULK CARGO LIQUEFACTION THE CAN TEST

POCKET CARD

www.nepia.com



@NorthPandiClub



The North of England
P&I Association Limited



The North of England
P&I Association Limited



North P&I Club

THE CAN TEST

- A rigid **cylindrical can** - (0.5 to 1 L capacity).
- **Half fill** with a sample of the material.
- Bring it down **sharply** from a height of about 0.2 m
- Repeat **25 times** - at **1 – 2 second intervals**.
- Take high definition pictures and video
- Examine the surface for free moisture or fluid conditions.
- If free moisture or a fluid condition appears **DO NOT LOAD** and **SEEK ADVICE**.
- www.nepia.com/bitesize-training

FOR FURTHER INFORMATION PLEASE CONTACT OUR LOSS PREVENTION TEAM ON
LOSS.PREVENTION@NEPIA.COM